

## Cationic Bitumen (Asphalt) Emulsion

Type: Slow-Setting

Grade: CSS-1

Standard: ASTM D2397/D2397M - 13



Property	Min	Max	Test Method
<b>Test on Emulsions</b>			
Viscosity, Saybolt Furol at 25 °C, SFS	20	100	ASTM D7496
Storage stability test, 24-h, %	-	1	ASTM D6930
Demulsibility, 35 mL, 0.8 % dioctyl sodium sulfosuccinate, %	-	-	ASTM D6936
Particle charge test	positive		ASTM D7402
Sieve test, %	-	0.1	ASTM D6933
Cement mixing test, %	-	2.0	ASTM D6935
<b>Distillation:</b>			
Oil distillate, by volume of emulsion, %	-	-	ASTM D6997
Residue, %	57	-	ASTM D6997
<b>Tests on residue from distillation test:</b>			
Penetration, 25°C (77°F), 100 g, 5 s	100	250	ASTM D5
Ductility, 25°C (77°F), 5 cm/min, cm	40	-	ASTM D113
Solubility in trichloroethylene, %	97.5	-	ASTM D2042