

Cutback Bitumen

Type : Slow-Curing

Grade : SC-250

Standard : ASTM D 2026M - 15



Property	Min	Max	Test Method
Kinematic viscosity at 60°C [140°F], mm ² /s	250	500	ASTM
Flash point (Cleveland open cup), °C [°F]	79	-	ASTM D92
Distillate test:			
Total distillate to 360°C [680°F], volume %	4	20	ASTM D402
Solubility, %	99		ASTM D2042
Kinematic viscosity on distillation residue at 60°C [140°F], mm ² /s	800	10000	ASTM D2170
Asphalt residue:			
Residue of 100 penetration, %	60		ASTM D243
Ductility of 100 penetration residue at 25°C [77°F], cm	100		ASTM D113
Water, %	-	0.5	ASTM D95

Applications:

Open-graded aggregate

Dense-graded aggregate

Patching, stockpile

Dust binder